## **Hook and Loop Ties**

## • TEXTIE-Series

As cables use thinner and softer insulation, and as fibre optic cables become more common, there is a need for a 'soft' method of bundling. TEXTIEs are ideal for use on telephone cables, optical fibre and network cables. In addition, they are perfect for use in temporary installations such as theatre stage construction or the manufacture of prototype cable harnesses.

TEXTIEs can also be used in many domestic and office applications, too.



- Quick and simple to use without tools
- No waste
- Resistant to ageing with no corrosion
- Re-usable up to 400 times
- Various colours for easy identification of multiple cable runs




One Step to the Web!



Due to the functional cable tie design the TEXTIE is fixed on the cable and can't get lost.



The TEXTIE-Series is available in different colours and lengths.



T) (DE	Width	Length	Bundle	Material	Material		Pack	
TYPE	(W)	(L)	Ø max.	Loop	Hook	Colour	Cont.	Article-No.
TEXTIE S	12.5	150.0	45.0	Polyamide (PA)	Polypropylene (PP)	Black (BK)	10	130-00012
	12.5	200.0	60.0	Polyamide (PA)	Polypropylene (PP)	Black (BK)	10	130-00013
TEXTIE M	12.5	200.0	60.0	Polyamide (PA)	Polypropylene (PP)	Blue (BU)	10	130-00018
	12.5	200.0	60.0	Polyamide (PA)	Polypropylene (PP)	Green (GN)	10	130-00017
I EXTIE IVI	12.5	200.0	60.0	Polyamide (PA)	Polypropylene (PP)	Red (RD)	10	130-00014
	12.5	200.0	60.0	Polyamide (PA)	Polypropylene (PP)	White (WH)	10	130-00021
	12.5	200.0	60.0	Polyamide (PA)	Polypropylene (PP)	Yellow (YE)	10	130-00016
TEXTIE L	12.5	330.0	100.0	Polyamide (PA)	Polypropylene (PP)	Black (BK)	10	130-00019
TEXTIE 5M	12.5	5,000.0	-	Polyamide (PA)	Polypropylene (PP)	Black (BK)	1	130-00020
TEXTIE 25M	13.0	25,000.0	-	Polyamide (PA)	Polypropylene (PP)	Black (BK)	1	130-00022

All dimensions in mm. Subject to technical changes.

Minimum Order Quantity (MOQ) may differ from package content. Other packaging options may also be available.

## **Material Specification Overview**

Material	Shortcut	Operating Temperature	Colour**	Flammability	Material Properties*	
Aluminium-alloy	AL	-40 °C to +180 °C	Natural (NA)		<ul><li>Corrosion resistant</li><li>Antimagnetic</li></ul>	RoHS
Chloroprene	CR	-20 °C to +80 °C	Black (BK)		<ul><li>Weather-resistant</li><li>High yield strength</li></ul>	RoHS
Ethylenterafluori- neethylen	E/TFE	-80 °C to +170 °C	Blue (BU)	UL94 V0	<ul> <li>Resistance to radioactivity</li> <li>UV- resistant, not moisture sentitive</li> <li>Good chemical resistance to:</li> <li>acids, bases, oxidizing agents</li> </ul>	RoHS
Polyacetal	POM	-40 °C to +90 °C, (+110 °C, 500 h)	Natural (NA)	UL94 HB	<ul> <li>Limited brittleness sensitivity</li> <li>Flexible at low temperature</li> <li>Not moisture sensitive</li> <li>Robust on impacts</li> </ul>	RoHS
Polyamide 11	PA11	-40 °C to +85 °C, (+105 °C, 500 h)	Black (BK)	UL94 HB	<ul> <li>Bio-plastic, derived from vegetable oil</li> <li>Strong impact resistance at low temperature</li> <li>Very low moisture absorption</li> <li>Weather-resistant</li> <li>Good chemical resistance</li> </ul>	RoHS HF
Polyamide 12	PA12	-40 °C to +85 °C, (+105 °C, 500 h)	Black (BK)	UL94 HB	<ul><li>Good chemical resistance to:</li><li>acids, bases, oxidizing agents</li><li>UV- resistant</li></ul>	RoHS HF
Polyamide 4.6	PA46	-40 °C to +150 °C (5000 h), +195 °C (500 h)	Natural (NA), Grey (GY)	UL94 V2	<ul><li>Resistance to high temperatures</li><li>Very moisture sensitive</li><li>Low smoke sensitive</li></ul>	RoHS HF LFH
Polyamide 6	PA6	-40 °C to +80 °C	Black (BK)	UL94 V2	High yield strength	RoHS
Polyamide 6.6	PA66	-40 °C to +85 °C, (+105 °C, 500 h)	Black (BK), Natural (NA)	UL94 V2	High yield strength	RoHS HF
<b>Polyamide 6.6,</b> Glassfibre reinforced	PA66GF13, PA66GF15	-40 °C to +105 °C	Black (BK)	UL94 HB	Good resistance to: lubricants, vehicle fuel, salt water and many solvents	RoHS HF
<b>Polyamide 6.6</b> heat and UV sta- bilised	PA66HSW	-40 °C to +105 °C	Black (BK)	UL94 V2	High yield strength     Modified elevated max. temperature     UV-resistant	RoHS HF
Polyamide 6.6 Heat Stabilised	PA66HS	-40 °C to +105 °C	Black (BK), Natural (NA)	UL94 V2	High yield strength     Modified elevated max. temperature	RoHS HF
<b>Polyamide 6.6</b> High Imp. Mod., Heat Stab.	PA66HIRHS	-40 °C to +105 °C	Black (BK)	UL94 HB	Limited brittleness sensitivity     Higher flexibility at low temperature     Modified elevated max. temperature	RoHS
<b>Polyamide 6.6</b> High Imp. Mod. scan black	PA66HIR(S)	-40 °C to +80 °C, (+105 °C, 500 h)	Black (BK)	UL94 HB	Limited brittleness sensitivity     Higher flexibility at low temperature	RoHS HF
<b>Polyamide 6.6</b> High Impact Modified	PA66HIR	-40 °C to +80 °C, (+105 °C, 500 h)	Black (BK)	UL94 HB	Limited brittleness sensitivity     Higher flexibility at low temperature	RoHS

Tefzel® is a registered trademark of DuPont.

General linguistic usage for cable ties made from raw material E/TFE is Tefzel®-Tie. In additon to Tefzel® from DuPont HellermannTyton is also using equivalent E/TFE raw material from other suppliers.

<sup>\*\*</sup>More colours on request.





<sup>\*</sup>These details are only rough guide values. They should be regarded as a material specification and are no substitute for a suitability test. Please see our datasheets for further details.

## **Material Specification Overview**

		are are		lity	*_	
Material	Shortcut	Operating Temperature	Colour**	Flammability	Material Properties*	
Polyamide 6.6 high impact modified, heat and UV stabilised	PA66- HIRHSW	-40 °C to +110 °C	Black (BK)	UL94 HB	Limited brittleness sensitivity     Higher flexibility at low temperature     Modified elevated max. temperature     High yield strength, UV-resistant	RoHS HF
<b>Polyamide 6.6</b> UV Resistant	PA66W	-40 °C to +85 °C, (+105 °C, 500 h)	Black (BK)	UL94 V2	High yield strength     UV-resistant	RoHS HF
Polyamide 6.6 V0	PA66V0	-40 °C to +85 °C	White (WH)	UL94 V0	<ul><li> High yield strength</li><li> Low smoke emission</li></ul>	RoHS HF LFH
<b>Polyamide 6.6 V0</b> High Oxygen Index	PA66- V0-HOI	-40 °C to +85 °C, (+105 °C, 500 h)	White (WH)	UL94 V0	<ul><li> High yield strength</li><li> Low smoke emissions</li></ul>	RoHS HF LFH
<b>Polyamide 6.6</b> with metal particles	PA66MP	-40 °C to +85 °C, (+105 °C, 500 h)	Blue (BU)	UL94 HB	High yield strength	RoHS HF
Polyamide 6 high impact mo- dified	PA6HIR	-40 °C to +80 °C	Black (BK)	UL94 HB	Limited brittleness sensitivity     Higher flexibility at low temperature	RoHS
Polyester	SP	-50 °C to +150 °C	Black (BK)		UV-resistant Good chemical resistance to: most acids, alkalis and oils	RoHS HF LFH
Polyetheretherke- tone	PEEK	-55 °C to +240 °C	Beige (BGE)	UL94 V0	Resistance to radioactivity  Not moisture sensitive Good chemical resistance to: acids, bases, oxidizing agents	RoHS HF LFH
Polyethylene	PE	-40 °C to +50 °C	Black (BK), Grey (GY)	UL94 HB	Low moisture absorption     Good chemical resistance to: most acids, alcohol and oils	RoHS HF
Polyolefin	РО	-40 °C to +90 °C	Black (BK)	UL94 V0	Low smoke emissions	RoHS HF LFH
Polypropylene	PP	-40 °C to +115 °C	Black (BK), Natural (NA)	UL94 HB	<ul><li>Floats in water</li><li>Moderate yield strength</li><li>Good chemical resistance to: organic acids</li></ul>	RoHS HF
Polypropylene, Ethylene-Propyle- ne-Dien-Terpoly- mere-rubber free of Nitrosamine	PP, EPDM	-20 °C to +95 °C	Black (BK)	UL94 HB	Good resistance to high temperatures     Good chemical and abrasion resistance	RoHS HF
Polyvinylchloride	PVC	-10 °C to +70 °C	Black (BK), Natural (NA)	UL94 V0	Low moisture absorption     Good chemical resistance to: acids, ethanol, oil	RoHS
Stainless Steel	SS304, SS316	-80 °C to +538 °C	Natural (NA)		Corrosion resistant     Antimagnetic	RoHS HF LFH
Thermoplastic Polyurethane	TPU	-40 °C to +85 °C	Black (BK)	UL94 HB	<ul><li> High elastic</li><li> Good chemical resistance to:</li><li> acids, bases, oxidizing agents</li></ul>	RoHS HF

Tefzel® is a registered trademark of DuPont.

General linguistic usage for cable ties made from raw material E/TFE is Tefzel®-Tie. In additon to Tefzel® from DuPont HellermannTyton is also using equivalent E/TFE raw material from other suppliers.

<sup>\*\*</sup>More colours on request.



<sup>\*</sup>These details are only rough guide values. They should be regarded as a material specification and are no substitute for a suitability test. Please see our datasheets for further details.